

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C06B 45/10, 25/34	A1	(11) International Publication Number: WO 00/03960 (43) International Publication Date: 27 January 2000 (27.01.00)
(21) International Application Number: PCT/US99/15395 (22) International Filing Date: 8 July 1999 (08.07.99) (30) Priority Data: 09/116,744 16 July 1998 (16.07.98) US (71) Applicant: ALLIANT TECHSYSTEMS INC. [US/US]; MN11-2216, 600 Second Street N.E., Hopkins, MN 55343-8384 (US). (72) Inventor: BROWN, Lisa. G.; 143 14th Street, Pulaski, VA 24301 (US). (74) Agent: MERSEREAU, C., G.; Nikolai, Mersereau & Dietz, P.A., 820 International Centre, 900 Second Street S., Minneapolis, MN 55402 (US).		(81) Designated States: AU, BR, CA, JP, ZA, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: HIGH ENERGY GUN PROPELLANTS (57) Abstract A low sensitivity gun propellant is disclosed having improved impetus and ballistic potential comprising RDX particles combined with at least one matrix component and plasticizer components including nitroglycerin and amounts of methyl nitrate ethyl nitramine and ethyl nitrate ethyl nitramine.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

HIGH ENERGY GUN PROPELLANTS BACKGROUND OF THE INVENTION

The invention was made with Government support under Contract No. DAA09-91-Z-001 with the Department of the Army, and, accordingly, the Government has certain rights in the invention.

I. Field of the Invention

The present invention is directed generally to improvements in high energy propellant compositions, particularly with regard to the use of alternate ingredients to improve energetic qualities and increase bulk loading density without increasing impact, shock or friction sensitivity. More particularly, the invention allows the use of a relatively large amount of 1, 3, 5-trinitro - 1, 3, 5-triaza - cyclohexane (cyclo trimethyl trinitramine) usually referred to as cyclonite or (RDX) in double-based compositions to increase energy output and achieve greater bulk loading densities without increasing impact, shock or friction sensitivity by adding the RDX in combination with an amount of nitrate ethyl nitramines (NENAs) as ingredients in the high energy propellants. In this manner, greater bulk loading densities and energy outputs are achieved without additional risk. The invention is particularly suitable for granular loaded tank ammunition.

II. Related Art

Most conventional propellants including propellants used in conventional artillery including 120 mm tank ammunition, and particularly those that are poly-based, use a matrix component, usually nitrocellulose (NC), in combination with nitroglycerine (NG), which also acts as a high energy plasticizer for the NC, together with an amount of an energy adjusting component such as an energetic solid exemplified by cyclo trimethyl trinitramine (RDX), cyclo tetramethyl trinitramine usually referred to as homocyclonite or (HMX), ethylene di-nitramine (EDNA), and others. Diethylene glycol dinitrate (DEGDN) and triethylene

-2-

glycol dinitrate (TEGDN) are also employed as conventional primary high energy adjustment components. However, the use of these materials in propellant formulae is discouraged because, while these materials enable a propellant to obtain and maintain a high energy level, they, at the same time, impose rather serious safety limitations as these materials may easily be set off or initiated by heat, impact and/or shock. Generally, efforts directed to reducing one or more of these sensitivities have also resulted in reducing the energetic output of the propellant. Heat sensitivity has proved to be somewhat less of a problem to overcome than impact or shock, however. RDX, for example, has a high shock but relatively low thermal sensitivity.

Plasticizers which have high energy output are known as high energy adjustment/plasticizing compounds (HEAPCs). These include NENAs and other such compounds. In the past, several approaches have been used in an effort to reduce the risks associated with sensitive materials while attempting to minimize the associated reduction in energetic output of the overall composition. One such approach has involved the elimination or very limited use of shock-sensitive high energy adjustment plasticizing compounds such as RDX, HMX and the like. In this manner, these components have been replaced with various other known high energy plasticizer components as plasticizers for nitrocellulose (NC), for example, including nitroglycerine (NG), acetyl triethyl citrate (ATEC) and a variety of nitrated acetals and others with some success.

However, RDX is a low cost primary high energy adjustment component with particularly desirable attributes. These include the ability to increase overall propellant impetus or performance and also to increase the density of the propellant grains which allows for greater bulk loading density in the shell case as compared to conventional propellants in similar geometries. Thus, if the sensitivity of the RDX-containing formulations could be

-3-

decreased without reducing or eliminating the RDX, formulae with superior performance could be achieved.

RDX has been added to JA-2, conventional tank and artillery propellant in the past to achieve advanced ballistic performance. However, it has been reported that researchers at Army Research Laboratory (ARL) found RDX crystals on the surface of the JA-X propellant during aging. These researchers theorize that the RDX, partially dissolved in the DEGDN fraction, was carried to the surface of the granules as the DEGDN began to leach out at higher temperatures. This crystalline growth on the surface is a significant sensitivity hazard, and greatly increases the likelihood of initiation due to unplanned mechanical stimuli. For this and other reasons, including the inherent sensitive nature of RDX, the use of RDX in artillery propellant compositions, has been generally discouraged.

The use of nitratro ethyl nitramine (NENA) compounds in propellant formulae is known. U.S. Patent 5,482,581 to Urenovitch discloses low vulnerability propellant (LOVA) containing mixtures of alkyl nitratro ethyl nitramines (alkyl NENAs) and/or bis (2-nitroxy-ethyl) nitramine (DINA) with nitrocellulose (NC). A further U.S. Patent to Zeigler, 5,520,756, also discloses the use of alkyl nitratro ethyl nitramine in combination in nitrocellulose/nitroguanidine double based propellants which may also contain cyclonites (RDX).

U.S. Patent 5,325,782 to Strauss et al incorporates a cyclic nitramine in the form of 2-nitroimino-5-nitro-hexahydro-1, 3, 5 triazine (NNHT) which may be combined with methyl and ethyl NENA, nitrocellulose and RDX. Dillehay et al (U.S. 5,487,851) also shows the possible use of alkyl NENA compounds in LOVA propellants which may contain RDX.

It would present an advantage if a significant amount of the low cost high energetic propellant ingredient RDX could be utilized to increase the propellant impetus and

-4-

loading density in a manner which does not cause the propellant composition to be more sensitive to heat, impact and/or shock. This is especially true with respect to munitions for tank guns.

5 Accordingly, it is a principal object of the present invention to obtain an insensitive, high energy polybased propellant composition.

It is also a principal object of the present invention to provide a propellant for artillery weapon systems having
10 improved energetic properties with respect to conventional JA-2 without sacrificing safety or increasing the sensitivity threshold initiation levels (TIL).

Another object of the invention is to increase the impetus of propellant compositions by adding a relatively
15 large amount of RDX without increasing the sensitivity of the propellant.

A further object of the invention is to provide artillery propellant matrices containing ethyl and methyl NENA in combination with relatively large amounts of RDX.

20 A still further object of the invention is to provide artillery propellant matrices including ethyl and methyl NENAs and RDX that offer impetus and shock sensitivity advantages over formulae using NG and DEGDN plasticizers.

Other objects and advantages will become apparent to
25 those skilled in the art upon becoming familiar with the present specification together with the appended claims.

SUMMARY OF THE INVENTION


The present invention attains the above and other objects by providing a multi-based propellant of improved
30 energy output that retains the low sensitivity characteristics of conventional double-based propellant compositions such as JA-2. This is accomplished in the detailed embodiments by utilizing a rather large fraction of RDX in combination with amounts of NENAs and
35 particularly ethyl and methyl NENAs to replace a fraction of the NC and NG and all of the DEGDN in the JA-2 or other such NC/NG double-based propellant containing DEGDN or

-5-

TEGDN as a primary high energy adjustment component. The amount of RDX that can be safely added is between about 20 percent and about 40 percent and the amount of NENAS is about 15 percent to 22 percent.

5 Ballistic simulations indicate that up to a 1.7 percent increase in muzzle velocity can be obtained using 19-perf hex granules based on bench scale batches of the material. Three experimental formulations containing approximately 25 percent, 30 percent and 34 percent 5-
10 micron particle size RDX (by weight), respectively, have been tested. These formulations have demonstrated the feasibility of combining RDX and NENAS to increase the impetus of propellants while retaining the sensitivity characteristics of conventional propellants such as JA-2.
15 Ballistic simulations indicate that the 1.7 percent increase in muzzle velocity can be obtained without increasing the sensitivity of the composition.

The preferred NENA compounds include nitrato ethyl nitramine of the formula



in which R is defined as a member selected from CH_3- and C_2H_5- .

25 The term "effective amount" as applied to the HEAPC component is defined as an amount of one or more nitrato ethyl nitramine(s) capable of forming a high energy colloided extrudable mass with a matrix component as herein defined and additionally capable of supplementing an active
30 amount of high energy adjustment components to obtain a lower level of both thermal and shock sensitivity.

The term "matrix component", for purposes of the present invention, is defined as one or more of a dehydratable nitrocellulose, cellulose acetate, cellulose
35 acetate butyrate(CAB), ethyl cellulose and the like, it being noted that the energy content between commercial batches of nitrocellulose often vary substantially and,

-6-

therefore, maximum permissible substitution with alternate, better-controlled matrix material of a less energetic type, such as the butyrate derivative (CAB) can provide substantial advantage in maintaining propellant batch consistency.

The term "primary high energy adjustment component", for purposes of the present invention, is defined as one or more of RDX, HMX, DEGDN and the like, which are utilized in combination with matrix and HEAPC components to obtain a desired energy level of a double (or triple)-based propellant product.

DETAILED DESCRIPTION

As stated above, the propellants of the present invention accomplish the assimilation of RDX in multi-based propellants in a manner which overcomes previous drawbacks which have heretofore discouraged the inclusion of any significant amount of RDX including its inherent impact, friction and shock sensitivity and its tendency to crystallize out of other formulations including those utilizing NG and DEGDN.

Table 1 depicts a comparison of propellant compositions and thermochemicals in which the conventional tank propellant JA-2 is compared with three examples of propellant made in accordance with the present invention. The three example formulations include RPD-20, RPD-21 and RPD-22. As can be seen from Table 1, the impetus (J/g) and ballistic potential $J/cc \times 10^{-3}$ of all three formulas are significantly higher than that measured for JA-2. The RPD-22 material is particularly noteworthy. In the formulas of the invention, the combination of 5-micron RDX and ethyl and methyl NENA are utilized to replace some of the nitroglycerin and all of the DEGDN in the JA-2 formulation.

-7-

Table 1. Comparison of Propellant Compositions and Thermochemicals

	INGREDIENTS	JA2	RPD20 (Measured)	RPDS21 (Measured)	RPDS22 (Measured)
	NC (13.15% N)	59.50	---	---	---
	NC(12.6% N)	---	41.90	36.48	31.11
5	RDX (5 micron)	---	25.71	30.33	34.08
	Methyl NENA	---	14.00	13.44	12.57
	Ethyl NENA	---	10.00	9.57	8.94
	NG	14.90	7.69	9.46	12.58
	DEGDN	24.80	---	---	---
10	Misc.	0.80	0.70	0.72	0.72
THERMOCHEMICALS					
	Flame Temp., K	3394	3372	3451	3551
	Impetus, J/g	1140.0	1205.6	1226.1	1249.1
	Gamma	1.2248	1.2366	1.2349	1.2324
15	Ballistic Potential J/cc x 10 ³	8.0	8.4	8.6	8.9
	HOE, cal/g	1123.3	1099.5	1129.7	1167.3

-8-

The three RPD formulations were processed through the evenspeed operation to evaluate the burn rates of the formulations. Table 2 is a summary of burn rate data for the three formulations at various temperatures. This burn
5 rate data was derived from 700cc closed bomb shots at 0.2 g/cc loading density. Note that RPD-22 offers the greatest ballistic advantage for advanced ammunition, specifically an M829A2 round based upon increased impetus, ballistic
10 JA-2. Ambient pressure closed bomb shots were also performed which confirm the extrapolated high pressure burn rates obtained from the 700cc bomb data.

Table 2. Burn Rate Comparison of Experimental Formulations

Burn Rate Parameters	RPD-20			RPD-21			RDD-22		
	-40 F	90 F	145 F	-40 F	90 F	145 F	-40 F	90 F	145 F
Exponent(n)	1.000	0.986	0.983	1.009	1.035	1.055	1.016	1.050	1.061
Coefficient(r)	0.0720	0.0832	0.0903	0.0675	0.0670	0.0642	0.0697	0.0664	0.0662

5

Burn rate data determined using 700 cc closed bomb at 0.2 loading density, where $r = a \cdot P^n$ and units are $r = \text{cm/s}$, $P = \text{MPa}$.

-10-

Further, during the processing of the three formulations, sensitivity testing was performed particularly on the RPD-22 paced because it was believed to be the most sensitive of the three experimental
5 formulations inasmuch as it has the highest RDX content. Testing was conducted prior to pre-rolling. Similarly, the pre-roll sheets were tested prior to introducing the sheets into the evenspeed roll mill.

-11-

Table 3.

Threshold Initiation Levels (TIL) for Various Propellants
to Mechanical Initiation Stimuli*

		Friction, lbs @ 8 fps	Impact, cm	ESD, J	TV, %	Th, mils
	JA-2	Paste	225	≥117	0.64	64
		Preroll	530	80	7.81	0.7
5	2R40 (JA-2 w/ 40% 7.5 micron RDX)	Paste	290	33	0.13	15.5
		Preroll	130	11	≥9.4	0.17
	M44	Paste	225	13	0.26	3.5
		Preroll	290	51	9.45	0.6
	RPD-22	Paste	≥950	64	**NA	9.5
		Preroll	225	64	≥9.5	1.5
10	APS-5 Double-Base Solventless	Paste	140	13	0.075	---
		Finished (dry)	140	11	0.075	---

* The Threshold Initiation Level (TIL) is defined as the highest energy level at which no initiation occurs as evidenced by 20 consecutive failures, with at least one initiation occurring at the next higher test level.

** NA - Not Available -- This test was not performed due the relatively high TV of the sample. The ESD TIL value for dry paste (with a TV of 0.05% and a 31 mil thickness) is 0.125 Joules.

-12-

Table 3 is a comparison of Threshold Initiation Levels (TIL) for JA-2, 2R40, M44 and RPD-22 in the paste and pre-roll process states. The table also includes the minimum sensitivity requirements for Aerospace Propulsion Standards (APS-5) for solventless propellant. It is noteworthy that RPD-22 is significantly less sensitive than the minimum sensitivity values in APS-5. Although a direct comparison between RPD-22 and JA-2 reveals that RPD-22 is more impact sensitive, some sensitivity discrepancies between propellants in Table 3 may be attributed to differences in sample thicknesses and moisture contents. In addition, RPD-22 appears less sensitive in the paste and pre-roll process states than does M44 and 2R40 (for the given total volatile content and thickness tested). Thus, testing on bench scale quantities of RPD-22 indicates that this material is generally superior to previous formulations.

-13-

Table 4. Results of IBHVG2 M829A2 Simulations

	JA-2	RPD-22		
Form	Combination of 19- perf kerfed	7-perf cyl	19-perf cyl	19-perf hex
Length, in	sticks, 7-perf	0.700	0.660	0.690
Web, in	sticks, and 7-perf	0.075	0.070	0.077
5 Perf Diameter, in	granules	0.031	0.030	0.030
Results of IBHVG2 Simulations (at Ambient)				
*Charge Weight, lb	18.86	17.00	17.50	18.00
Muzzle Velocity, ft/s	5539	5555	5565	5634
Peak Pressure, kpsi	87.4	87.4	87.3	87.2

- 10 RPD formulations are between 3.8 and 5.0% more dense than conventional JA-2. This increase in density allows for greater bulk loading densities in the granular form.

-14-

Table 4 presents a summary of IBHVG2 M829A2 simulations comparing the current JA-2 kerfed stick charge with RPD-22 and various granulations. This directly illustrates the increase in performance made possible with the three new formulations. Note that the 19-perf hex RPD-22 granulation offers a 1.7 percent increase in muzzle velocity (98 ft/s) at ambient as compared to firing with a JA-2 charge. The RPD formulations are between 3.8 percent and 5.0 percent more dense than conventional JA-2. This higher density allows for greater bulk loading densities in the granular form.

Generally, a propellant containing from about 20 percent to 40 percent (weight) of RDX and 15 percent to 30 percent (weight) of combined methyl and ethyl NENA fractions is preferred. The most preferred range appears to be from about 30 percent to 40 percent (weight) RDX and about 18 percent to 24 percent (weight) total ethyl and methyl NENA. The methyl NENA fraction is preferably about 40 percent greater than the ethyl fraction. The preferred size of the RDX is about 5 microns.

What is claimed is:

-15-

CLAIMS

1. A low sensitivity gun propellant having improved impetus and ballistic potential comprising RDX particles combined with at least one matrix component and plasticizer components including nitroglycerin and amounts of methyl
5 nitrato ethyl nitramine and ethyl nitrate ethyl nitramine.
2. The propellant of claim 1 wherein the amount by weight of RDX is from 20 percent to 40 percent and the amount (weight) of methyl and ethyl nitrato ethyl
10 nitramines is from 15 percent to 30 percent.
3. The propellant of claim 1 wherein the matrix component is nitrocellulose.
4. The propellant of claim 2 wherein the ratio of methyl nitrato ethyl nitramine to ethyl nitrato nitramine
15 is about 1.4 to 1.
5. The propellant of claim 2 wherein the amount by weight of RDX is about 35 percent and the amount (weight) of methyl and ethyl nitrate ethyl nitramines is about 21.5 percent.
- 20 6. The propellant of claim 5 wherein the ratio of methyl nitrate ethyl nitramine to ethyl nitrate nitramine is about 1.4 to 1.
7. The propellant of claim 2 wherein the amount of nitroglycerin is from about 7 percent to about 13 percent.
- 25 8. The propellant of claim 5 wherein the amount of nitroglycerin is about 12.5 percent.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/15395

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C06B45/10 C06B25/34

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C06B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 95 17358 A (THIOL CORPORATION) 29 June 1995 (1995-06-29) claims & US 5 487 851 A cited in the application	1-8
A	CHEMICAL ABSTRACTS, vol. 125, no. 14, 30 September 1996 (1996-09-30) Columbus, Ohio, US; abstract no. 172469a, R.L. SIMMONS: "Effect of plasticizer on performance of XM-39 LOVA" page 302; XP000664709 abstract & Int. Annu. Conf. ICT 1996, 27th(Energetic Materials), 53.1-53.4 --- -/-	1



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

22 September 1999

Date of mailing of the international search report

29/09/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Schut, R

INTE TIONAL SEARCH REPORT

Int. Patent Application No.
PCT/US 99/15395

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 482 581 A (J.V. URENOVITCH) 9 January 1996 (1996-01-09) cited in the application claims ---	1
A	EP 0 490 258 A (HERCULES INCORPORATED) 17 June 1992 (1992-06-17) claims & US 5 520 756 A cited in the application ---	1
A	CHEMICAL ABSTRACTS, vol. 122, no. 24, 12 June 1995 (1995-06-12) Columbus, Ohio, US; abstract no. 294736u, R.V. CARTWRIGHT: "Volatility of NENA and other energetic plasticizers determined by thermogravimetric analysis" page 233; XP000663789 abstract & PROPELLANTS, EXPLOS., PYROTECH., vol. 20, no. 2, 1995, pages 51-57, ---	1
A	DE 37 44 680 A (ROYAL ORDNANCE PLC.) 28 November 1991 (1991-11-28) page 2, line 2 - line 29 page 5, line 40 - line 61 ---	1
A	EP 0 353 961 A (MORTON THIOKOL, INC.) 7 February 1990 (1990-02-07) page 3, line 39 - line 51; claims -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/15395

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9517358	A	29-06-1995	US 5487851 A	30-01-1996
			AU 679837 B	10-07-1997
			AU 1595495 A	10-07-1995
			BR 9408495 A	26-08-1997
			CA 2179389 A	29-06-1995
			EP 0735990 A	09-10-1996
			JP 9506853 T	08-07-1997
			US 5565150 A	15-10-1996
US 5482581	A	09-01-1996	NONE	
EP 490258	A	17-06-1992	CA 2053832 A	12-06-1992
			DE 69107970 D	13-04-1995
			DE 69107970 T	03-08-1995
			JP 4265291 A	21-09-1992
			US 5520756 A	28-05-1996
DE 3744680	A	28-11-1991	AU 663677 A	19-10-1995
			BE 1005565 A	15-06-1993
			CA 1325518 A	28-12-1993
			FR 2664587 A	17-01-1992
			GB 2243826 A, B	13-11-1991
			IT 1235712 B	24-09-1992
			NL 8715010 A	01-10-1991
			SE 500687 C	08-08-1994
			SE 8801944 A	06-09-1991
			US 5500060 A	19-03-1996
EP 353961	A	07-02-1990	US 4976794 A	11-12-1990
			US 4919737 A	24-04-1990
			AU 607888 B	14-03-1991
			AU 3829989 A	08-02-1990
			CA 1333526 A	20-12-1994
			DE 68925245 D	08-02-1996
			DE 68925245 T	11-07-1996
			JP 2088486 A	28-03-1990